



**Era Polymers Pty. Ltd.**  
25-27 Green Street, Banksmeadow  
Sydney, NSW 2019  
AUSTRALIA  
www.erapol.com.au

## Erapol E83A

POLYETHER (PTMEG) TDI PREPOLYMER

### TECHNICAL DATASHEET

**Erapol E83A** is a liquid isocyanate terminated pre-polymer based on PTMEG polyol.

Polymers made from **Erapol E83A** exhibit outstanding resilience, low hysteresis and heat build up as well as excellent hydrolysis resistance.

#### Application

**Erapol E83A** has a high resilience and is suitable for mining applications, particularly in slurry applications such as pipelining, pump impellers, floatation equipment etc.

**Erapol E83A** elastomers show excellent low temperature resistance, making them suitable for applications involving service temperatures below 0°C (up to - 60°C), e.g. Wheels and tyres.

#### Product Specification

<b>% NCO</b>	3.10 ± 0.25
<b>Specific Gravity @ 25°C</b>	1.05
<b>Viscosity @ 80°C (cps)</b>	1000 - 1500
<b>Colour</b>	Clear, light amber

#### Mixing and Curing Conditions

		<b>E83A / MOCA</b>	<b>E83A / Ethacure 300</b>	<b>E83A / Eracure 110</b>
<b>Erapol E83A</b>	(pph)	100	100	100
<b>MOCA Level</b>	(pph)	10.0	-	-
<b>Ethacure 300 Level</b>	(pph)	-	8.0	-
<b>Eracure 110 Level</b>	(pph)	-	-	8.4
<b>Recommended % Theory</b>		100	100	100
<b>Erapol Temperature</b>	(°C)	75 - 85	65 - 75	65 - 75
<b>Curative Temperature</b>	(°C)	110 - 120	20 - 30	20 - 30
<b>Pot Life</b>	(mins)	15	12	10
<b>Demould Time @ 100°C</b>	(hrs)	1	1	2 - 4
<b>Post Cure Time @ 100°C</b>	(hrs)	16	16	16



This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

## Physical Properties

Properties presented below are to be used as a guide and not intended for specification purposes.

		E83A / MOCA	E83A / E300*	E83A / E110**	TEST METHOD
<b>Hardness</b>	(Shore A)	83 ± 3	83	80	AS1683.15
<b>Tensile Strength</b>	MPa (psi)	33.0 (4786)	32.0 (4641)	32.0 (4641)	AS1683.11
<b>100% Modulus</b>	MPa (psi)	4.6 (667)	4.6 (667)	4.8 (696)	AS1683.11
<b>300% Modulus</b>	MPa (psi)	8.3 (1204)	6.9 (1001)	8.0 (1160)	AS1683.11
<b>Angle Tear Strength, Die C</b>	(kN/m)	72	65	69	AS1683.12
<b>Trouser Tear Strength</b>	(kN/m)	27	24	22	AS1683.12
<b>Elongation</b>	(%)	550	450	545	AS1683.11
<b>DIN Resilience</b>	(%)	62	61	62	DIN53512
<b>DIN Abrasion Resistance 10N</b>	(mm <sup>3</sup> )	35	41	21	AS1683.21
<b>DIN Abrasion Resistance 5N</b>	(mm <sup>3</sup> )	12	18	10	AS1683.21
<b>Compression Set / 22 hr @ 70°C</b>	(%)	28	40	-	AS1683.13
<b>Cured Specific Gravity</b>	(g/cm <sup>3</sup> )	1.08	1.08	1.10	AS1683.4

Please note \* Ethacure 300  
\*\* Eracure 110

## Processing Procedure

1. **Erapol E83A** should be heated to 80 ± 5°C and thoroughly degassed at 1 - 5 mm Hg of vacuum until excessive foaming stops.
2. The curative should be added to **E83A**, the MOCA must first be melted at 110 - 120°C prior to mixing and Ethacure 300/Eracure 110 processed at room temperature. After adding the curative, mix thoroughly, being careful not to introduce air into the mixture.
3. Pour mixed materials into moulds that have been preheated to 80 - 100°C and pre-coated with release agent.

## Adhesion

Adhesion of Erapol based elastomers to various substrates is at best marginal if a primer is not used. Please consult Era Polymers for specific recommendations to improve adhesion.

## Handling Precautions

**Erapol E83A** contains small amounts of free TDI. Therefore the product should be used in well-ventilated areas. Avoid breathing in vapours and protect skin and eyes from contact.

In case of skin contact, immediately remove excess, wash with soap and water. For eye contact, immediately flush with water for at least 15 minutes. Call a physician.

If nose, throat or lungs become irritated from breathing in vapours, remove exposed person to fresh air. Call a physician.