



Era Polymers Pty. Ltd.
25-27 Green Street, Banksmeadow
Sydney, NSW 2019
AUSTRALIA
www.erapol.com.au

Erapol L-E95A

POLYETHER (PTMEG) TDI PREPOLYMER

TECHNICAL DATASHEET

Erapol L-E95A is a liquid isocyanate terminated pre-polymer based on PTMEG polyether polyol.

Polymers made from **Erapol L-E95A** exhibit outstanding abrasion, impact and chemical resistance, along with high load bearing capacity.

Moreover, **Erapol L-E95A** is a lower free TDI version of Erapol E95A.

Application

Typical uses of this polymer include sheeting, forklift truck tyres, rolls, and gears, die pads etc.

Product Specification

% NCO	6.00 ± 0.20
Specific Gravity at 25°C	1.07
Viscosity at 80°C (cps)	300 - 700
Colour	Clear, light amber

Mixing and Curing Conditions

		L-E95A / MOCA	L-E95A / Ethacure 300	L-E95A / Eracure 110
Erapol L-E95A	(pph)	100	100	100
MOCA Level	(pph)	18.0	-	-
Ethacure 300 Level	(pph)	-	14.5	-
Eracure 110 Level	(pph)	-	-	15.4
Recommended % Theory		95	95	95
Erapol Temperature	(°C)	75 - 85	65 - 75	65 - 75
Curative Temperature	(°C)	110 - 120	20 - 30	20 - 30
Pot Life	(mins)	6 - 10	4 - 8	6 - 7
Demould Time at 100°C	(mins)	30 - 60	30 - 60	45 - 60
Post Cure Time at 100°C	(hrs)	16	16	16



This information is of general nature and is supplied without recommendation or guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

Physical Properties

Properties presented below are to be used as a guide and not intended for specification purposes.

		L-E95A / MOCA	L-E95A / E300*	L-E95A / E110**	TEST METHOD
Hardness	(Shore A)	95 ± 3	93 ± 3	93 ± 3	AS1683.15
Tensile Strength	MPa (psi)	36 (5221)	35.0 (5076)	33.5 (4859)	AS1683.11
100% Modulus	MPa (psi)	12.5 (1813)	11.1 (1610)	10.1 (1465)	AS1683.11
300% Modulus	MPa (psi)	20.4 (2959)	18.6 (2698)	19.6 (2843)	AS1683.11
Angle Tear Strength, Die C	(kN/m)	112	108	108	AS1683.12
Trouser Tear Strength	(kN/m)	59	67	62	AS1683.12
Elongation	(%)	490	530	520	AS1683.11
DIN Resilience	(%)	42	44	49	DIN53512
DIN Abrasion Resistance 10N	(mm ³)	54	51	57	AS1683.21
Compression Set / 22 hr at 70°C	(%)	37	-	-	AS1683.13
Cured Specific Gravity	(g/cm ³)	1.12	1.12	1.11	AS1683.4

Please note * Ethacure 300

** Eracure 110

Processing Procedure

1. **Erapol L-E95A** should be heated to 80 ± 5°C and thoroughly degassed at -95 kpa of vacuum until excessive foaming stops.
2. The curative should be added to **L-E95A**, the MOCA must first be melted at 110 - 120°C prior to mixing and Ethacure 300/Eracure 110 processed at room temperature. After adding the curative, mix thoroughly, being careful not to introduce air into the mixture.
3. Pour mixed materials into moulds that have been preheated to 80 - 100°C and pre-coated with release agent.

Adhesion

Adhesion of Erapol based elastomers to various substrates is at best marginal if a primer is not used. Please consult Era Polymers for specific recommendations to improve adhesion.

Handling Precautions

Erapol L-E95A contains small amounts of free TDI. Therefore the product should be used in well-ventilated areas. Avoid breathing in vapours and protect skin and eyes from contact.

In case of skin contact, immediately remove excess, wash with soap and water. For eye contact, immediately flush with water for at least 15 minutes. Call a physician.

If nose, throat or lungs become irritated from breathing in vapours, remove exposed person to fresh air. Call a physician.